



Product Information Sheet



Sheet Number: **0075**

Rev 22-11-06

ROOFBOND Flexible Pointing

Acrylic water based flexible pointing for roof tiles and ridges caps

Roofbond Flexible Pointing

Roofbond Flexible Pointing is an acrylic compound deigned to point ridge caps on concrete and terracotta roof tiles. Roofbond Flexible Pointing comes in a range of colours and is applied by pointing trowel. This product is warranted for 10 years.

General Application Guide:

Apply Roofbond Flexible Pointing using an suitable pointing trowel to ridge cap sides and noses as well as three and four way caps.

Substrate Application Information:

Clean surfaces thoroughly.

Fill holes with sand/cement mortar NOT Roofbond Flexible Pointing. Roofbond is ready to use. Colour can be added if required.

To "wet up" Roofbond Flexible Pointing DO NOT add water, just agitate with a trowel.

Point approx. 1 metre of ridge capping and trowel to a steeled finish. Lubricate trowel with water.

Apply at up to 5 mm thick. Greater thickness increases drying time, sagging and cost. Collars should be conservative and just sufficient to seal the cap overlap.

Weep holes should be put in before curing has progressed too far.

Sponging is not recommended except for bed and point gables. Thin with water to a slurry and sponge on.

For cold climate usage or if rain is imminent, cement with white cement for lighter colors. It can be added at the rate of 375ml (one drink can) per 10 litre bucket, as a slurry. Note -cement is not required under warm/dry conditions.

NOTES:

Clean up: Clean tools with water before Roofbond Flexible Pointing has dried.

Drying time: On warm days Roofbond Flexible Pointing will be water-resistant after 2 hours. Allow longer curing time for low temperatures and high humidity conditions.

Never apply if rain is likely within two hours.

Caution: Do not use when temperature is below 5°C. Do not store in direct sunlight. Keep lid tightly affixed.



Specifications:

(all dry times are considered at 25° C and at 50% humidity)

Roofbond:

Surface Dry: 4 -5 hours

Top Coat: 12 hours

Hard Dry: 4 -5 days

Wet Film Thickness: 3-5mm

Dry Film Thickness: 3-5mm

Thinning: No thinning required normally. If desired thin with water sparingly.

Clean Up: Clean up with water



Top Picture: Roofbond Flexible Pointing.

Bottom Picture: Roofbond Fleible Pointing and Roofbond Painted Tile Roof.

Roofbond Flexible Pointing comes in 15 litre pails.

See **MSDS for safety information**

Features:

Excellent Adhesion

Choice of Colours

Flexible

Easy To Apply

Durable

Pre Mixed

Best on Market

Benefits:

Good mechanical fastening of ridges

Suits most roof colours

Allows for some substrate move-

Trowel glides over compound

Warranted for 10 years

Stirring only required

Using what others use.

Notes: There are many substrates on the market. Please consult Shieldcoat for further information regarding applications not on this sheet.