



# Product Information Sheet



Sheet Number: **0060**  
Rev 7-4 -2010



## Roofbond Roofing Paint

Acrylic water based roof paint

**Safe to collect rain water for drinking after 7 days**

### Features:

- High Gloss /Hard Finish
- Choice of Colours
- Flexible
- Easy To Apply
- Durable
- Environmentally friendly
- Available in Thermobond Heat Reflective Version

### Roofbond:

Roofbond Roofpaint is a premium, quality acrylic roof coating designed to coat or recoat all roofing substrates. Has been extensively tested for outstanding durability for one of the harshest climates in the world. Our coatings are engineered and guaranteed to last at least 10 years

**Note:** Disconnect down pipes for water collection and reconnect 7 days after job completion in collecting water for drinking.

### Substrate Application Information:

#### Fibre Cement:

- Apply Mouldshield C cleaner diluted 5:1 with water
- Soft broom and hose off. Do not water blast.
- Apply 1 coat of Shieldseal W Plus with 517 airless tip
- Apply one coat of Fillabond (if required for porous or pitted roofs)
- Apply 2 coats of Roofbond Roofing Paint with 521 airless tip.

#### Concrete Tile:

- Water blast roof with at least 3000 p.s.i.
- Apply one coat of Shieldseal W with 517 airless tip
- Apply one coat of Fillabond (if required for porous or pitted roofs)
- Apply 2 coats of Roofbond Roofing Paint with 521 airless tip

#### Factory Painted Metal– Zinc Metal

- Water blast roof with at least 3000 p.s.i.
- Apply one coat of Shieldseal W plus with 517 airless tip
- Apply 2 coats of Roofbond Roofing Paint with 521 airless tip

#### Rusty Galvanized Metal:

- Clean loose rust wit a wire brush
- Water blast roof with at least 3000 p.s.i.
- Apply one coat of Rustshield W with 517 airless tip
- Apply 2 coats of Roofbond Roofing Paint with 521 airless tip

**Notes:** It is optional to use Rustshield T where Rustshiheld W used. Rustsheild T is solvent based and requires 24 hrs drying.

**Notes:** There are many substrates on the market. Please consult Shieldcoat for further information regarding applications



### Specifications:

(all dry times are considered at 25C and at 50% humidity)

#### Roofbond:

**Surface Dry:** 2 hours

**Top Coat:** 2 hours

**Hard Dry:** 4 -5 days

**Wet Film Thickness:** Approx. 180 microns

**Dry Film Thickness:** Approx. 90 microns

**Thinning:** No thinning required normally. If desired thin with water sparingly.

**Clean Up:** Clean up with water



Top Picture: Roofbond Roofing Paint on a Metal Roof

Bottom Picture: Roofbond Roofing Paint on concrete tile

Available in 15 litre pails. Gloss or Low Seen

### Benefits:

- Dirt resistant Easy To Clean
- Suits all Decors
- Allows for some substrate move-
- Airless Sprayed
- Warranted for 10 years
- Aids in reducing carbon footprint
- Thermobond Reduces cavity temp.

Shieldcoat has become the first paint manufacturer in Australia to meet the international environmental standard, ISO 14001

See MSDS for safety information