



SHIELDCOAT PTY LTD
Unit 2/1075 Beaudesert Rd, Archerfield Q 4108
Phone: (07) 3274 6911 Fax: (07) 3274 6414
Email: info@shieldcoat.com.au Web: www.shieldcoat.com.au

Application Methods: **RUSTSHIELD AL**
Anti-corrosive primer

NOTE: For applications where roof to be painted is used for collecting drinking water, ensure at least seven (7) days or the first rain before reconnecting downpipes.

 **STEPS:**

- Ensure surface is dry, clean and as free as possible of contaminants such as grease and detergent.
- Remove all loose rust. There is no need to remove light or spot rust, only scale rust.
- Apply one coat
- Allow at least 2 hours to dry
- Apply second coat

 **NOTES:**

- Rustshield AL** is suitable for over Zincalume, Colorbond, mild, cast, wrought gal and pre-primed steel.
- Rustshield AL** should be stored out of direct sunlight. Settling is likely after prolonged storage - stir thoroughly before use.
- Coverage is approx. 130 sq. metres per 20 litres.
- If brushing apply liberally and avoid leaving runs.
- Airless spraying is the recommended method of application, applied thinly using a 517 tip
- Clean up with mineral turpentine.
- Important: Do not dilute.

Shieldcoat is firmly committed to providing product and service of the highest quality and consistency.

Last modified on: 31/12/02

DISCLAIMER

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.